

calculation in accordance to EN 410

date : 13.09.2012  
database version : 08.12.2011 / K  
version : 3.0

## Glazing from outside to inside

37.52 mm

<b>pane1</b>	substrate	Guardian LamiGlass ExtraClear 4(0.76)4, 8.76 mm
<b>spacer/gas1</b>		22 mm / air 10%, argon 90%
<b>pane2</b>	coating on pos.3	Guardian ClimaGuard N
	substrate	Guardian LamiGlass ExtraClear 3(0.76)3, 6.76 mm (EN 410)

## Results

<b>UV :</b>		
transmittance [%] :		$\tau_{UV} = 0,1$
<b>light :</b>		
transmittance for standard illuminant D65 [%] :		$\tau_V = 78,7$
reflectance for standard illuminant D65 [%] (*) :		$\rho_V = 11,6$
reflectance for standard illuminant D65 [%] (**):		$\rho_V = 11,3$
general colour rendering index [%] :		$R_a = 97,2$
<b>energy :</b>		
solar direct transmittance [%] :		$\tau_e = 51,2$
solar direct reflectance [%] (*) :		$\rho_e = 19,5$
solar direct reflectance [%] (**):		$\rho_e = 20,4$
solar direct absorption [%] (*) :		$a = 29,3$
secondary internal heat transfer factor [%] (*) :		$q_i = 9,0$
total solar energy transmittance (solar factor) [%] (*) :		$g = 60,2$
shading coefficient (=g/0,87) (*) :		$sc = 0,69$
thermal conductance (U-value) [W/m <sup>2</sup> K] (EN 673):		$U_g = 1,2$
slope [°] : $\alpha=90,0$		
(*) incident radiation from the outside		
(**) incident radiation from the inside		

**The calculated values are for orientation only and do not offer any guarantee regarding the fabrication of the un- intended end- product.**

**Glass configurations do not amount to a guarantee of product availability.**