

calculation in accordance to EN 410

date : 13.09.2012  
database version : 08.12.2011 / K  
version : 3.0

## Glazing from outside to inside

24.00 mm

<b>pane1</b>	substrate	Guardian Float Glass ExtraClear, 4.00 mm
	coating on pos.2	Guardian ClimaGuard Solar
<b>spacer/gas1</b>		16 mm / air 10%, argon 90%
<b>pane2</b>	substrate	Guardian Float Glass ExtraClear, 4.00 mm

## Results

<b>UV :</b>		
transmittance [%] :		$\tau_{UV} = 25,7$
<b>light :</b>		
transmittance for standard illuminant D65 [%] :		$\tau_V = 66,9$
reflectance for standard illuminant D65 [%] (*) :		$\rho_V = 26,6$
reflectance for standard illuminant D65 [%] (**):		$\rho_V = 24,2$
general colour rendering index [%] :		$R_a = 96,1$
<b>energy :</b>		
solar direct transmittance [%] :		$\tau_e = 40,6$
solar direct reflectance [%] (*) :		$\rho_e = 43,4$
solar direct reflectance [%] (**):		$\rho_e = 42,8$
solar direct absorption [%] (*) :		$a = 16,0$
secondary internal heat transfer factor [%] (*) :		$q_i = 1,9$
total solar energy transmittance (solar factor) [%] (*) :		$g = 42,5$
shading coefficient (=g/0,87) (*) :		$sc = 0,49$
thermal conductance (U-value) [W/m <sup>2</sup> K] (EN 673):		$U_g = 1,0$
slope [°] : $\alpha=90,0$		
(*) incident radiation from the outside		
(**) incident radiation from the inside		

**The calculated values are for orientation only and do not offer any guarantee regarding the fabrication of the un- intended end- product.**

**Glass configurations do not amount to a guarantee of product availability.**